

Calofer

Revision: 2/06/2022

Page 1 from 2

Technical data

Basis	Sodium silicate
Consistency	Stable paste
Curing system	Physical drying
Density	1,82 g/ml
Maximum allowed distortion	Ca. 2 %
Temperature resistance**	-40 °C → 1500 °C
Application temperature	5 °C → 30 °C

* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. ** This information relates to fully cured product.

Product description

Calofer is a high quality sealing paste based on sodium silicate.

porous surfaces improves the adhesion.

We recommend a preliminary adhesion test on any substrate.

Properties

- Ready for use
- Not elastic after curing
- No fragmentation or cracking after curing
- Heat resistant up to 1500°C
- Free of asbestos
- Not suitable for permanently standing water
- Suitable for interior applications

Joint dimensions

Min. width for joints: 5 mm

Max. width for joints: 15 mm

Applications

- Sealing of joints and openings where high temperatures are possible.
- Sealing of stoves, ovens, fireplaces.

Application method

Application method: Apply with spatula, filling knife or sealing gun.

Cleaning: Before curing, Calofer can be removed with water from substrates and tools.

Finishing: Finish with a spatula or putty knife.

Repair: With the same material.

Packaging

Colour: anthracite

Packaging: 290 ml cartridge, 300 ml cartridge, 310 ml cartridge

Health- and Safety Recommendations

Take the usual labour hygiene into account.

Consult label and material safety data sheet for more information.

Dangerous. Respect the precautions for use.

Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C. Protect against frost.

Remarks

- A slight warming of the heating installation during 12 hours after application prevents bubbleforming and improves structure.
- With prolonged exposure to very high temperatures, the color may lighten.

Substrates

Substrates: brick, concrete, metals

Nature: rigid, clean, dry, free of dust and grease.

Surface preparation: Slightly moistening

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

Calofer

Revision: 2/06/2022

Page 2 from 2

Liability

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.